



專業導熱材料生產廠  
Professional TIM Manufacturer  
<http://www.ziitek.com>

# TCP™100-01PP Thermally Conductive plastic

TCP™100-01PP is a Thermally Conductive Engineering Plastic developed for the housing design which requires high thermally conductivity and reduces the weight more than 30% comparing with the same aluminium devices.



## Application

TCP™100-01PP can be used in applications such as Heat Sinking Housing at LED-lit BLU in LCD/LED TV and LED-lit lamps such as MR16. Also it can replace the normal Aluminum heat sink.

## Features

- 》 Good thermal conductivity: **0.8W/mK**
- 》 Excellent thermal conductivity compared to normal engineering plastics
- 》 Lighter than normal Aluminum housing 30% in weight
- 》 Excellent mould ability in injection moulding

## Typical Properties of TCP™100-01PP

Items	Test method	Unit	Typical data
<b>Physical Properties</b>			
Color	Visual	****	Gray
Melt index	ASTM D1238	g/10min	14.73
Specific Gravity	ASTM D792	g/cm <sup>3</sup>	1.55
Shrinkage	ASTM D955	%	1.3
<b>Mechanical Properties</b>			
Tensile Strength	ASTM D638	MPa	9.92
Flexural Strength	ASTM D790	MPa	38
Flexural Modulus	ASTM D790	MPa	3900
Impact Strength, notched	GB/T 1483-2008	kJ/m <sup>2</sup>	8.9
<b>Electrical Properties</b>			
Dielectric Breakdown Voltage	ASTM D149	VAC	>10000
Dielectric Constant, 1MHz	ASTM D150	****	3.1
Volume Resistivity	ASTM D257	Ohm-meter	7.0 X 10 <sup>12</sup>
<b>Thermal Properties</b>			
Heat Deflection Temperature	ASTM D648	°C	130
Thermal Conductivity Through Plane	ASTM E1461	W/m-K	0.8
Flame retardancy	Min. thick. 1.0mm	Class	V-0

\*These are typical values and should not be used for establishing product specification. The properties may vary upon the machine process under use. For more information please contact Ziitek Tech directly.

[Click](#) | [Gap Filler](#) | [Phase Change](#) | [Thermal Insulator](#) | [Thermal Greases](#) | [Thermal Tape](#) | [Thermal Plastic](#) | [Potting](#)



**Canada:**

TEL:+001-604-2998559

E-mail: [sales@thermazig.com](mailto:sales@thermazig.com)

<http://www.thermazig.com>

**Taiwan:**

TEL: +886-2-22771007

E-mail: [sales@ziitek.com.tw](mailto:sales@ziitek.com.tw)

<http://www.ziitek.com.tw>

**Dongguan:**

TEL: +86-769-38801208

E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)

<http://www.ziitek.com>

**Kunshan:**

TEL: +86-512-57816297

E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)

<http://www.ziitek.com>

**Chengdu:**

TEL: +86-28-62379168

E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)

<http://www.ziitek.com>

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their

TCP™100-01PP Injection parameters		Value Range
Barrel Zone Temperature	One sect / °C	180-220°C
	Two sect / °C	190-230°C
	Three sect / °C	180-220°C
Mouth Temperature / °C		200-230°C
Melt Temperature / °C		200-240°C
Bake Temperature / °C		80-90°C 2H
Mould Temperature / °C		According to the machine tonnage
Injection Pressure / Bar		
Injection Speed / mm/s		Medium Speed
Remarks: Data from the laboratory of the Division I ① above are for reference only, not as a product standard reference. ② The typical processing conditions according to different models, different mold and product requirements to make the appropriate adj		

## Handling & Safety

TCP™100 should be used in accordance with good industrial practice. For more detailed information please contact Ziitek technical service group.

## Supply Appearance And Standard Packing

TCP™100 is supplied in regular pellet form packaged in polyethylene bags. Net weight is 25kg per bag. For more information please contact us.

Click → | [Gap Filler](#) | [Phase Change](#) | [Thermal Insulator](#) | [Thermal Greases](#) | [Thermal Tape](#) | [Thermal Plastic](#) | [Potting](#)



**Canada:**

TEL: +001-604-2998559  
E-mail: [sales@thermazig.com](mailto:sales@thermazig.com)  
<http://www.thermazig.com>

**Taiwan:**

TEL: +886-2-22999766  
E-mail: [sales@ziitek.com.tw](mailto:sales@ziitek.com.tw)  
<http://www.ziitek.com.tw>

**Dongguan:**

TEL: +86-769-81017480  
E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)  
<http://www.ziitek.com>

**Kunshan:**

TEL: +86-512-57816297  
E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)

**Chengdu:**

TEL: +86-28-62379168  
E-mail: [sales@ziitek.com](mailto:sales@ziitek.com)

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.